

S355jrg2 steel properties

s355jrg2 steel properties are highly regarded in the steel industry for their excellent combination of strength, ductility, and weldability. This structural steel grade is widely used across various engineering and construction applications due to its versatile characteristics. Understanding the properties of s355jrg2 steel is essential for engineers, architects, and manufacturers to ensure the material's suitability for specific projects. This article provides an in-depth overview of s355jrg2 steel properties, including its chemical composition, mechanical characteristics, applications, and processing features.

Overview of S355JRG2 Steel

S355JRG2 is a structural steel grade classified under the European Standard EN 10025-2. It is part of the S355 series, which is known for its high yield strength and good toughness. The "JRG2" designation indicates specific impact toughness and weldability requirements, making it suitable for demanding structural applications.

This grade is often used in the construction of bridges, cranes, offshore platforms, and large-scale infrastructure projects. Its excellent weldability and formability make it a preferred choice for fabricators and engineers aiming for durable and reliable structures.

Chemical Composition of S355JRG2 Steel

The chemical makeup of s355jrg2 steel significantly influences its mechanical properties and weldability. The standard specifies the following typical composition ranges:

Key Elements in S355JRG2 Steel

- **Carbon (C):** ? 0.20%. Ensures adequate strength while maintaining good weldability.
- **Silicon (Si):** 0.10% ? 0.55%. Contributes to deoxidation and strength.
- **Manganese (Mn):** 1.00% ? 1.60%. Enhances strength and toughness.
- **Phosphorus (P):** ? 0.025%. Kept low to improve toughness.
- **Sulfur (S):** ? 0.015%. Minimized to prevent brittleness.
- **Additional Elements:** Small amounts of niobium, vanadium, and titanium may be present to improve grain refinement and strength.

The controlled chemical composition ensures that s355jrg2 maintains a balance between strength and ductility, making it suitable for structural applications requiring impact resistance.

Mechanical Properties of S355JRG2 Steel

The mechanical properties of s355jrg2 steel are critical for its performance under load and in various environmental conditions. These properties are defined by standards and test results, ensuring consistent quality across batches.

Yield Strength

- The minimum yield strength of s355jrg2 steel is typically 355 MPa (megapascals). This high yield point allows structures to withstand significant stress without permanent deformation.

Ultimate Tensile Strength

- The tensile strength generally ranges from 470 to 630 MPa, depending on the thickness and specific manufacturing process. This ensures durability under tension and bending forces.

Ductility and Toughness

- High ductility enables the steel to deform without fracturing, which is vital for absorbing energy during impacts or seismic activity.
- Impact toughness, especially for the JRG2 grade, is tested to be high at various temperatures, confirming its reliability in cold environments.

Hardness

- Typically falls within the moderate range, ensuring the steel is resistant to wear yet remains workable for welding and forming processes.

Physical and Processing Properties

Understanding the physical and processing characteristics of s355jrg2 steel is essential for effective fabrication and application.

Density and Thermal Conductivity

- Density: approximately 7.85 g/cm³, typical for carbon steels.

- Thermal conductivity: about 50 W/m·K, facilitating heat transfer during welding and cutting.

Weldability

- S355JRG2 exhibits excellent weldability without requiring preheating in most cases, thanks to its controlled carbon content and alloying elements.
- Suitable welding methods include MIG, MAG, and arc welding, making it versatile for fabrication.

Formability and Machinability

- The steel can be readily formed into various shapes through bending, rolling, and pressing.
- Machining is manageable with standard tools, though high-strength grades may require specific techniques to avoid tool wear.

Applications of S355JRG2 Steel

The distinct properties of s355jrg2 steel make it suitable for numerous structural and engineering applications.

Structural Engineering

- Used extensively in constructing bridges, high-rise buildings, and frameworks due to its high strength-to-weight ratio.
- Ideal for load-bearing structures where safety and durability are paramount.

Offshore and Marine Structures

- The toughness and corrosion resistance of s355jrg2 make it suitable for offshore platforms, ships, and subsea equipment.
- Its ability to withstand harsh environments ensures long service life.

Heavy Equipment and Machinery

- Components such as cranes, excavators, and industrial machinery benefit from the steel's strength, weldability, and impact resistance.

Other Uses

- Fabrication of storage tanks, pressure vessels, and transport containers.
- Structural components in railway and transportation infrastructure.

Advantages of S355JRG2 Steel

Choosing s355jrg2 steel offers several benefits:

- **High Strength:** Supports the construction of large, durable structures.
- **Good Ductility:** Enables deformation without cracking, essential for seismic zones.
- **Excellent Weldability:** Simplifies fabrication and reduces costs.
- **Impact Resistance:** Maintains toughness even at low temperatures.
- **Versatility:** Suitable for a wide range of structural and industrial applications.

Considerations When Using S355JRG2 Steel

While s355jrg2 steel offers numerous advantages, certain considerations are necessary to maximize its performance:

Heat Treatment

- Typically, the steel does not require extensive heat treatment, but post-welding heat treatments like stress relieving can improve residual stresses.

Corrosion Protection

- Although relatively resistant, additional coatings or galvanization may be necessary for marine or highly corrosive environments.

Handling and Storage

- Proper handling prevents surface damage that could affect weld quality or structural integrity.
- Storage in dry, covered areas helps prevent rust formation.

Summary

In conclusion, **s355jrg2 steel properties** highlight its status as a robust, reliable, and versatile structural steel grade. Its excellent combination of high yield strength, good toughness, weldability, and formability makes it suitable for a broad spectrum of engineering applications, from large infrastructure projects to offshore platforms. Understanding its chemical composition, mechanical characteristics, and processing features enables engineers and fabricators to optimize its use for safety, durability, and efficiency.

Ensuring the correct application and handling of s355jrg2 steel will lead to the successful realization of complex structures that stand the test of time and environmental challenges. Whether in construction, heavy machinery, or marine engineering, s355jrg2 remains a preferred choice for modern steel solutions.

S355JRG2 Steel Properties: An In-Depth Guide for Engineers and Fabricators

When it comes to structural steel grades, S355JRG2 steel properties stand out as a versatile and reliable choice for a wide array of engineering and construction applications. Known for its impressive combination of strength, weldability, and toughness, S355JRG2 is a popular structural steel grade used across industries such as construction, bridge building, and heavy machinery manufacturing. Understanding its properties, standards, and suitable applications is essential for engineers, architects, and fabricators aiming to optimize safety, performance, and cost-efficiency in their projects.

What is S355JRG2 Steel?

S355JRG2 steel belongs to the S355 series of structural steels defined by the European standard EN 10025-2. The designation "S355" indicates a minimum yield strength of 355 MPa, making it a high-strength low-alloy (HSLA) steel. The additional suffixes denote specific characteristics:

- J: Impact test temperature of -20°C, indicating good toughness at low temperatures.
- R: Resistance to brittle fracture, especially important in cold environments.
- G2: Indicates the type of impact test specimen used; G2 refers to a specific testing standard.

In particular, S355JRG2 is a normalized steel grade with enhanced toughness and weldability, suitable for structural applications that demand high strength and ductility.

Chemical Composition of S355JRG2 Steel

Understanding the chemical makeup of S355JRG2 steel is fundamental to appreciating its properties. The typical chemical composition is as follows:

- Carbon (C): $\approx 0.20\%$
- Manganese (Mn): 1.60% to 1.85%
- Phosphorus (P): $\approx 0.025\%$
- Sulfur (S): $\approx 0.015\%$
- Nitrogen (N): Usually low, influencing weldability and toughness
- Additional Elements: Small amounts of copper, niobium, vanadium, and titanium may be present, contributing to strength and grain refinement

This chemical composition strikes a balance between strength, ductility, and weldability, making S355JRG2 suitable for demanding structural applications.

Mechanical Properties of S355JRG2 Steel

The mechanical properties define how the steel behaves under various loads and conditions. Key parameters include:

- Yield Strength
 - Minimum of 355 MPa (as indicated by the grade S355)
 - Ensures that the steel can withstand significant compressive or tensile forces without permanent deformation
- Tensile Strength
 - Typically ranges from 470 MPa to 630 MPa
 - Provides a safety margin for structural integrity under operational loads
- Ductility
 - Elongation at fracture: Usually $\approx 20\%$ in 5.65× ϕ A test
 - Indicates good ability to deform plastically before fracture, essential for absorbing energy and preventing sudden failure
- Impact Toughness

- At -20°C, the steel exhibits excellent toughness, with impact energy often exceeding 27 Joules
- Critical for cold-weather applications where brittle fracture risks are higher

- Hardness

- Typically around 160-200 HB (Brinell Hardness)
- Ensures resistance to surface wear and deformation

Physical and Thermal Properties

Aside from mechanical attributes, the physical and thermal characteristics influence how S355JRG2 behaves in different environments:

- Density: Approximately 7.85 g/cm³
- Young's Modulus: Around 210 GPa
- Thermal Conductivity: About 50 W/m·K at room temperature
- Coefficient of Thermal Expansion: Approximate value of 12×10^{-6} /°C

These properties are crucial for thermal analysis, design considerations involving temperature fluctuations, and assessing how the material interacts with other structural components.

Welding and Fabrication

One of the key advantages of S355JRG2 steel is its excellent weldability, thanks to its chemical composition and controlled toughness characteristics. For optimal welding results:

- Use proper preheating (typically around 80°C) to reduce the risk of cracks
- Avoid excessive heat input during welding to prevent grain growth and loss of toughness
- Employ suitable welding methods such as MAG/MIG, TIG, or submerged arc welding depending on the application

Post-weld heat treatment isn't usually necessary, but in critical structures, stress relief may be performed to minimize residual stresses.

Fabrication Considerations:

- Cutting: Suitable for plasma, oxy-fuel, and laser cutting
- Bending: Good ductility allows for bending without cracking
- Forming: Can be formed into various shapes with standard procedures

Standard and Certification Details

S355JRG2 steel conforms to the European standard EN 10025-2, which specifies technical delivery conditions for hot-rolled structural steels. The key features include:

- Mechanical property requirements
- Chemical composition limits
- Impact test requirements at specified temperatures

It is also certified according to various international standards, ensuring compliance with safety and quality benchmarks.

Typical Applications of S355JRG2 Steel

Given its properties, S355JRG2 is suited for numerous structural and engineering applications, including:

- Bridge Construction: Its toughness at low temperatures makes it ideal for bridges in cold climates
- Offshore Structures: Resistance to brittle fracture and good weldability support offshore platforms and oil/gas exploration equipment
- Buildings and Infrastructure: Used in frames, supports, and load-bearing structures
- Heavy Machinery: Components requiring high strength and ductility
- Mining and Earthmoving Equipment: Durable and resilient for harsh environments

Advantages and Limitations

Advantages:

- High yield and tensile strength
- Good toughness, even at low temperatures
- Excellent weldability and formability
- Good corrosion resistance when properly coated or painted
- Cost-effective compared to higher alloy steels

Limitations:

- Moderate weld metal hardness, requiring careful welding procedures
- Not suitable for very high-temperature environments where creep resistance is needed
- May require surface treatment to prevent corrosion in aggressive environments

Final Thoughts: Why Choose S355JRG2 Steel?

The S355JRG2 steel properties make it a top choice for structural engineers seeking a combination of strength, toughness, and versatility. Its compliance with European standards assures quality and consistency, while its mechanical and physical qualities support safe, durable, and efficient construction. Proper understanding of its welding, fabrication, and application parameters ensures that projects utilizing S355JRG2 steel maximize performance and longevity.

Whether constructing resilient bridges, offshore platforms, or industrial buildings, engineers can rely on S355JRG2 steel to meet demanding specifications and environmental conditions, making it an integral component of modern structural engineering.

In summary, S355JRG2 steel is a robust, adaptable, and reliable structural material that balances strength, toughness, and weldability. Its well-understood properties and compliance with international standards make it a preferred choice across a broad spectrum of engineering applications.

Question What are the main mechanical properties of S355JRG2 steel? S355JRG2 steel exhibits high yield strength (around 355 MPa), good tensile strength, excellent toughness, and good weldability, making it suitable for structural applications. **Answer** What does the 'JRG2' designation indicate in S355JRG2 steel? The 'JRG2' indicates that the steel has a Charpy impact test value of 27 Joules at -20°C, with 'J' referring to the impact test, 'R' indicating it is resistant to brittle fracture, and 'G2' denoting specific impact energy requirements. Is S355JRG2 steel suitable for welding applications? Yes, S355JRG2 steel has good weldability, making it suitable for various welding processes, provided proper procedures are followed to prevent issues like cracking. What are the typical applications of S355JRG2 steel? S355JRG2 steel is commonly used in structural engineering, bridges, heavy machinery, shipbuilding, and offshore structures due to its strength and toughness. What are the corrosion resistance properties of S355JRG2 steel? While S355JRG2 has good mechanical properties, its corrosion resistance is typical of mild carbon steels and may require protective coatings or treatments for outdoor or corrosive environments. What temperature range is suitable for the use of S355JRG2 steel? S355JRG2 steel performs well at ambient and moderately low temperatures, with Charpy impact properties maintained at -20°C; however, it is not suitable for extremely low temperature applications. How does S355JRG2 steel compare to other S355 grades? Compared to other S355 grades, S355JRG2 has standardized impact toughness at -20°C and is

specifically suited for structures requiring enhanced toughness in colder environments. Can S355JRG2 steel be used in offshore environments? While it has good mechanical properties, S355JRG2 is not inherently corrosion-resistant and typically requires protective coatings for offshore or marine applications. What are the chemical composition limits of S355JRG2 steel? S355JRG2 steel typically contains max 0.22% carbon, with controlled amounts of manganese, phosphorus, sulfur, and other elements to achieve its desired mechanical properties and toughness. Is S355JRG2 steel compliant with international standards? Yes, S355JRG2 steel complies with EN 10025-2 standards, which specify the technical delivery conditions for non-alloy structural steels.

Related keywords: mechanical properties, chemical composition, weldability, tensile strength, yield strength, corrosion resistance, heat treatment, structural applications, ductility, impact toughness

Sae 10b21 steel properties

Understanding SAE 10B21 Steel Properties

SAE 10B21 steel properties are integral to its widespread use across various industries due to its unique combination of strength, machinability, and versatility. This alloy belongs to the family of free-machining steels, which are designed to facilitate efficient manufacturing processes while maintaining reliable mechanical characteristics. Whether used in automotive components, machinery parts, or structural elements, understanding the specific properties of SAE 10B21 steel helps engineers and manufacturers optimize its application.

What is SAE 10B21 Steel?

SAE 10B21 steel is a low-carbon, free-machining alloy steel classified under the SAE (Society of Automotive Engineers) numbering system. Its composition is tailored to enhance machinability without significantly compromising other mechanical features. This steel grade is known for its excellent machinability, good strength, and acceptable ductility, making it suitable for precision machining applications.

Composition of SAE 10B21 Steel

The typical chemical composition of SAE 10B21 steel includes:

- Carbon (C): 0.10% ? 0.15%
- Manganese (Mn): 0.60% ? 0.80%

- Lead (Pb): up to 0.35% (added for machinability)
- Sulfur (S): up to 0.05%
- Other elements: Minor traces of phosphorus and silicon

The addition of lead is a defining characteristic, significantly improving the steel's machinability.

Mechanical Properties of SAE 10B21 Steel

Understanding the mechanical properties of SAE 10B21 steel is crucial for determining its suitability for specific applications. These properties include tensile strength, hardness, ductility, and impact resistance.

Tensile Strength and Hardness

- Tensile Strength: Typically ranges from 70,000 to 90,000 psi (480 to 620 MPa)
- Hardness: Usually falls within 70 to 120 HRB (Rockwell B scale), depending on heat treatment and processing

Ductility and Toughness

SAE 10B21 exhibits moderate ductility, allowing it to deform under stress without fracturing. Its toughness is sufficient for most machining applications, though it is not designed for high-impact or heavy-load conditions.

Impact Resistance

While not primarily an impact-resistant steel, SAE 10B21 maintains acceptable levels of toughness, especially when properly heat-treated, making it suitable for components that experience moderate shocks or vibrations.

Physical and Chemical Properties

The physical and chemical characteristics of SAE 10B21 steel influence its behavior during processing and service.

Physical Properties

- Density: Approximately 7.85 g/cm³
- Melting Point: Around 1425°C to 1540°C (2597°F to 2800°F)

- Thermal Conductivity: Moderate, facilitating heat dissipation during machining

Chemical Resistance

SAE 10B21 steel offers good corrosion resistance relative to other carbon steels, mainly when coated or treated. However, it is not considered corrosion-proof and should be protected in aggressive environments.

Machinability and Welding Characteristics

Machinability

One of the standout features of SAE 10B21 steel is its exceptional machinability, primarily due to the inclusion of lead and sulfur. The key points include:

- High machinability rating: Often rated as 85% or higher compared to free-cutting steels
- Smooth cutting action: Reduced tool wear and higher cutting speeds
- Ease of forming threads and precision parts: Ideal for manufacturing screws, bolts, and small machined components

Welding

While SAE 10B21 can be welded, it requires careful consideration:

- Preheating: Recommended to prevent cracking
- Welding techniques: Shielded metal arc welding (SMAW) or gas metal arc welding (GMAW) are suitable
- Post-weld treatment: Necessary to restore mechanical properties and relieve stresses

Heat Treatment and Processing

Proper heat treatment enhances the mechanical properties of SAE 10B21 steel, tailoring it for specific applications.

Heat Treatment Procedures

- Annealing: To improve machinability and relieve stresses
- Normalizing: To refine grain structure and improve toughness

- Hardening and Tempering: Achieved through quenching in oil or air, followed by tempering, to increase strength and hardness

Machining and Forming

Due to its free-machining nature, SAE 10B21 is easy to machine using standard tools, with minimal formation of built-up edges. It can be cold worked and shaped into various forms with relative ease.

Applications of SAE 10B21 Steel

The unique properties of SAE 10B21 steel make it suitable for a broad range of industrial applications, including:

Automotive Industry

- Manufacturing of fasteners like bolts, nuts, and screws
- Precision machined engine components
- Gear and shaft components requiring good machinability

General Manufacturing

- Small machinery parts
- Valves and fittings
- Tools and dies designed for mass production

Other Industries

- Electrical components
- Mechanical hardware
- Sporting equipment where lightweight and machinability are valued

Advantages and Disadvantages of SAE 10B21 Steel

Advantages

- Exceptional machinability: Reduces manufacturing time and tool wear
- Good strength-to-weight ratio: Suitable for lightweight components

- Versatile processing options: Can be heat-treated, welded, and formed with relative ease
- Cost-effective: Widely available and economical

Disadvantages

- Limited corrosion resistance: Requires protective coatings or treatments for harsh environments
- Not suitable for high-impact applications: May fracture under sudden shocks
- Lead content: Environmental and health concerns regarding lead use in manufacturing

Comparing SAE 10B21 with Other Steel Grades

Understanding how SAE 10B21 stacks up against other steels helps in selecting the right material:

| Feature | SAE 10B21 | SAE 1018 | 4140 Alloy Steel |

|-----|-----|-----|-----|

| Machinability | Excellent | Good | Moderate |

| Strength | Moderate | Moderate | High |

| Hardness | Up to 120 HRB | Up to 90 HRB | Up to 250 HB |

| Corrosion Resistance | Moderate | Moderate | Low |

SAE 10B21 excels in machinability but may lack the strength and corrosion resistance of higher alloy steels like 4140.

Conclusion

SAE 10B21 steel properties make it a popular choice for applications requiring excellent machinability combined with decent mechanical strength. Its low carbon content, coupled with the addition of lead, facilitates high-speed machining and precision manufacturing, especially for small parts such as fasteners, fittings, and components in the automotive sector.

Understanding its composition, mechanical and physical properties, and processing techniques enables engineers and manufacturers to optimize its use effectively. While it offers many advantages, considerations around corrosion resistance and environmental impact should guide its application choices.

In summary, SAE 10B21 steel remains a versatile, cost-effective alloy suitable for a wide array of industrial applications, especially where machining efficiency and moderate mechanical properties are paramount. Proper heat treatment and protective measures can further enhance its performance, ensuring reliable and durable components across various sectors.

SAE 10B21 Steel Properties: An In-Depth Analysis

SAE 10B21 steel is a versatile alloy that finds extensive application across various industries due to its unique combination of mechanical properties, weldability, and machinability. Understanding its characteristics is essential for engineers, material scientists, and manufacturing professionals seeking optimal performance for their specific applications. This comprehensive review delves into the fundamental properties, chemical composition, mechanical characteristics, heat treatment processes, and typical use cases of SAE 10B21 steel.

Introduction to SAE 10B21 Steel

SAE 10B21 steel is classified within the family of low-carbon, alloyed steels, often categorized under the AISI/SAE numbering system as a 1021 grade. Its designation indicates a carbon content of approximately 0.18-0.23%, combined with specific alloying elements that enhance its mechanical properties and weldability. This steel type is renowned for its good ductility, machinability, and moderate strength, making it a popular choice for manufacturing components that require a balance of workability and strength.

Chemical Composition

A detailed understanding of the chemical makeup of SAE 10B21 steel is fundamental to appreciating its properties:

- Carbon (C): 0.18-0.23%
- Provides tensile strength and hardness.
- Plays a vital role in hardenability and wear resistance.
- Manganese (Mn): 0.60-0.90%
- Enhances hardenability.
- Improves tensile strength and toughness.
- Phosphorus (P): Max 0.035%
- Generally kept low to improve weldability and toughness.
- Sulfur (S): Max 0.055%
- Usually minimized as it can reduce ductility but may be present to improve machinability.
- Other Elements:
- Possible small amounts of silicon, nickel, or chromium but typically in trace quantities unless

specified for particular properties.

This specific composition provides a good balance between strength, ductility, and machinability, making SAE 10B21 suitable for various manufacturing processes.

Mechanical Properties of SAE 10B21 Steel

The mechanical behavior of SAE 10B21 steel is characterized by several key properties, which are influenced by its chemical composition and heat treatment:

1. Tensile Strength

- Typically ranges from 370 MPa to 620 MPa (54,000 to 90,000 psi).
- The exact value depends on the processing method and heat treatment applied.
- Suitable for applications requiring moderate to high strength.

2. Yield Strength

- Usually between 235 MPa and 415 MPa (34,000 to 60,000 psi).
- Indicates the stress at which permanent deformation begins.
- Good for structural applications where some elastic deformation is acceptable.

3. Hardness

- As-rolled or normalized steel usually exhibits hardness in the range of 120-170 HB (Brinell Hardness).
- Through heat treatment (quenching and tempering), hardness can be increased significantly, often exceeding 200 HB.

4. Ductility and Toughness

- Exhibits good ductility, with elongation values typically around 20-25% in a 2-inch gauge length.
- The toughness is adequate for many structural and mechanical components, balancing strength with the ability to absorb energy during impact.

5. Fatigue Resistance

- Suitable for cyclic loading applications where fatigue life is a consideration.
- Proper heat treatment and surface finishing can enhance fatigue performance.

Heat Treatment and Its Effects

Heat treatment significantly influences the properties of SAE 10B21 steel. Common processes include:

1. Normalizing

- Heating to approximately 870°C (1600°F) followed by air cooling.
- Refines grain structure, improves toughness, and relieves internal stresses.

2. Quenching and Tempering

- Quenching from austenitizing temperature (~820-870°C / 1500-1600°F) in oil or air.
- Followed by tempering at 550-650°C (1020-1200°F).
- Results in increased strength and hardness, with controlled ductility.

3. Case Hardening

- Suitable for components requiring surface hardness while maintaining core toughness.
- Methods include carburizing or nitriding.

4. Impact of Heat Treatment

- Enhances mechanical properties, especially hardness and tensile strength.
- Proper tempering ensures a good balance between hardness and toughness, preventing brittleness.

Weldability and Machinability

SAE 10B21 steel is known for its commendable weldability, primarily due to its low carbon content and controlled alloying elements:

- Weldability:

- Can be welded using most common welding methods such as shielded metal arc welding (SMAW), gas metal arc welding (GMAW), and gas tungsten arc welding (GTAW).
- Preheating (around 100°C to 200°C) is recommended to minimize thermal stresses.
- Post-weld heat treatment may be necessary for high-stress applications.
- Machinability:
 - Excellent machinability due to its low carbon content and alloying elements.
 - Suitable for turning, drilling, and milling operations.
 - Use of cutting fluids helps improve tool life and surface finish.

Corrosion Resistance

While SAE 10B21 steel is not inherently corrosion-resistant, its corrosion behavior depends on environmental exposure:

- General Corrosion:
 - Susceptible to rust when exposed to moisture and oxygen.
 - Proper protective coatings or platings are recommended for outdoor or humid environments.
- Alloying Enhancements:
 - Addition of chromium or nickel can improve corrosion resistance, but in standard SAE 10B21, these are minimal.
- Maintenance:
 - Regular cleaning and application of protective coatings extend service life in corrosive environments.

Applications of SAE 10B21 Steel

SAE 10B21 steel's combination of properties makes it suitable for a wide array of applications:

- Automotive Components
 - Shafts, gears, and axles.
- Structural Parts
 - Frames, braces, and machinery supports.
- Machinery Parts

- Bolts, nuts, and fittings that require moderate strength.
- Tools and Dies
- Cutting tools and dies benefiting from its machinability.
- Hardware and Fasteners
- Nuts, bolts, and similar fasteners where ease of fabrication is essential.

Its adaptability and balance of properties make SAE 10B21 a preferred choice in many manufacturing scenarios.

Advantages and Limitations

Advantages:

- Good balance of strength, ductility, and machinability.
- Excellent weldability with proper procedures.
- Cost-effective for many applications.
- Readily available and easy to process.

Limitations:

- Limited corrosion resistance; not suitable for highly corrosive environments.
- Moderate hardness achievable without heat treatment.
- Not suitable for high-temperature applications requiring heat resistance.

Summary and Final Thoughts

SAE 10B21 steel stands out as a reliable, versatile alloy that bridges the gap between low-carbon steels and higher alloyed steels. Its chemical composition imparts a harmonious blend of mechanical properties, making it suitable for components that require moderate strength, good machinability, and weldability. Proper heat treatment can further enhance its performance, tailoring it to specific application needs.

Understanding its properties enables engineers and manufacturers to optimize design, processing, and performance, ensuring that SAE 10B21 steel is employed to its fullest potential. Whether in automotive, structural, or machinery applications, this steel grade offers an excellent combination of features that support many industrial requirements.

In conclusion, SAE 10B21 steel exemplifies a well-rounded material choice, balancing ease of fabrication with dependable mechanical performance. Its widespread use across industries

underscores its importance in modern manufacturing and engineering solutions.

QuestionAnswer What are the key mechanical properties of SAE 10B21 steel? SAE 10B21 steel exhibits good tensile strength, typically around 80,000 to 100,000 psi, along with excellent ductility and toughness. It also offers moderate hardness and good machinability, making it suitable for various industrial applications. What are the common uses of SAE 10B21 steel? SAE 10B21 steel is commonly used in manufacturing of mechanical components, automotive parts, and structural applications where moderate strength and good machinability are required. Its properties make it suitable for gears, shafts, and other precision parts. How does the composition of SAE 10B21 steel influence its properties? SAE 10B21 steel contains approximately 0.10% carbon and 0.20% boron, which enhance hardenability and strength. The boron addition improves the steel's response to heat treatment, resulting in improved hardness and wear resistance. Is SAE 10B21 steel heat-treatable, and what heat treatment processes are recommended? Yes, SAE 10B21 steel is heat-treatable. Recommended processes include quenching and tempering to achieve desired hardness and strength. Proper heat treatment enhances its machinability, toughness, and wear resistance. What are the corrosion resistance characteristics of SAE 10B21 steel? SAE 10B21 steel has moderate corrosion resistance, but it is not considered stainless. Protective coatings or surface treatments are often recommended to improve corrosion resistance in aggressive environments.

Related keywords: SAE 10B21 steel, 10B21 steel composition, 10B21 steel strength, 10B21 steel hardness, 10B21 steel applications, 10B21 steel corrosion resistance, 10B21 steel weldability, 10B21 steel machinability, SAE steel grades, 10B21 steel tensile properties

Aisi 4145 steel astm equivalent

aisi 4145 steel astm equivalent

Understanding the different grades of steel and their standards is essential for engineers, manufacturers, and procurement specialists. When it comes to AISI 4145 steel, one of the most common inquiries is its ASTM equivalent. Knowing the ASTM equivalent of AISI 4145 steel helps ensure compatibility, meet regulatory requirements, and select the right material for specific applications. This article provides a comprehensive overview of AISI 4145 steel, its properties, and its ASTM equivalents, offering valuable insights for professionals in the steel and manufacturing industries.

Introduction to AISI 4145 Steel

What is AISI 4145 Steel?

AISI 4145 steel is a chromium-molybdenum alloy steel known for its high strength, toughness, and excellent hardenability. It is commonly used in the manufacturing of components that require high tensile strength, wear resistance, and fatigue resistance, such as gears, shafts, and structural parts.

Main Characteristics of AISI 4145 Steel

- Chemical Composition:
- Carbon (C): 0.43-0.50%
- Chromium (Cr): 0.80-1.10%
- Molybdenum (Mo): 0.20-0.30%
- Manganese (Mn): 0.60-1.00%
- Silicon (Si): 0.15-0.35%
- Sulfur (S): Max 0.040%
- Phosphorus (P): Max 0.040%

- Mechanical Properties:
- High tensile strength
- Good ductility
- Excellent hardenability

- Heat Treatment: Suitable for various heat treatments like quenching and tempering to enhance specific properties.

- Applications: Used in manufacturing gears, shafts, axles, and other components requiring high strength and toughness.

ASTM Standards and Their Role

ASTM International develops and publishes technical standards for a wide range of materials, including steels. ASTM standards specify chemical compositions, mechanical properties, testing methods, and other criteria to ensure material quality and performance.

When selecting materials for critical applications, it is vital to identify ASTM equivalents to ensure compliance, compatibility, and optimal performance.

ASTM Equivalent Grades of AISI 4145 Steel

Understanding the Equivalence

Steel grades from different standards often have similar chemical compositions and mechanical properties but are designated differently. The ASTM standards most relevant to alloy steels like AISI 4145 include ASTM A29, ASTM A193, ASTM A320, and ASTM A105. However, for the specific chemical composition and mechanical properties of AISI 4145, the most common ASTM equivalent is ASTM A182 Grade F22.

Primary ASTM Equivalent: ASTM A182 Grade F22

- ASTM A182 Grade F22

- Composition: Similar to AISI 4145, with comparable chromium and molybdenum content.
- Application: Often used for high-temperature and high-pressure applications, such as flanges, valves, and fittings.
- Properties: High strength, good toughness, and excellent hardenability.

Other Related ASTM Grades

While ASTM A182 F22 is the primary equivalent, other grades can sometimes serve as substitutes depending on specific requirements:

- ASTM A29 4140 / 4145

- This specification covers alloy steel bars, plates, and shapes.
- 4140 steels are similar but may have slight variations in chemical composition.

- ASTM A193 Grade B7

- Used primarily for fasteners, but shares some properties with 4145, especially after heat treatment.

- ASTM A320 Grade L7

- For low-temperature service applications, with similar alloying elements.

Note: Always verify chemical composition and mechanical properties before substituting grades to

ensure suitability.

Comparison of Chemical Composition

Understanding the chemical composition helps determine the interchangeability of steel grades.

Element	AISI 4145 (%)	ASTM A182 F22 (%)	Remarks
Carbon (C)	0.43-0.50	0.20-0.30	Slightly higher in 4145, contributing to higher strength
Chromium (Cr)	0.80-1.10	1.00-1.50	Similar, with F22 sometimes having higher chromium for corrosion resistance
Molybdenum (Mo)	0.20-0.30	0.15-0.25	Similar, enhances hardenability
Manganese (Mn)	0.60-1.00	0.60-0.90	Comparable
Silicon (Si)	0.15-0.35	0.15-0.40	Similar

Implication: The chemical compositions are close enough for these grades to be used interchangeably in many applications, provided mechanical properties and heat treatments are also aligned.

Mechanical Properties and Heat Treatment

Typical Mechanical Properties

Property	AISI 4145	ASTM A182 F22
Tensile Strength	850-1000 MPa	690-930 MPa
Yield Strength	~620 MPa	~450 MPa
Hardness (after heat treatment)	Up to 50 HRC	Similar, depending on heat treatment

Heat Treatment Processes

- Quenching and Tempering: Enhances hardness, strength, and toughness.
- Annealing: Improves ductility and machinability.
- Normalization: Refines grain structure for better toughness.

The heat treatment procedures are similar across grades, and the choice depends on the desired mechanical properties for specific applications.

Applications and Suitability of ASTM Equivalents

Knowing the ASTM equivalent of AISI 4145 steel is crucial when sourcing materials for projects requiring compliance with American standards. Below are typical applications where these grades are suitable:

- **High-Strength Components** ? Gears, shafts, and axles in automotive and industrial machinery.
- **Structural Parts** ? Structural steel in construction that demands high tensile strength.
- **Pressure Vessels and Piping** ? For high-pressure and high-temperature environments, especially when using ASTM A182 F22.
- **Oil and Gas Industry** ? Components exposed to harsh environments, benefiting from the alloy's toughness.

Choosing the right ASTM grade depends on:

- Mechanical property requirements
- Environmental conditions
- Specific standards compliance
- Cost considerations

Procurement and Quality Assurance

When procuring AISI 4145 steel or its ASTM equivalents, consider the following:

- **Certification:** Ensure the supplier provides proper mill test reports (MTRs) verifying chemical composition and mechanical properties.
- **Standards Compliance:** Confirm that the material meets relevant ASTM standards such as ASTM A182, A29, or A193.
- **Heat Treatment Documentation:** Verify heat treatment procedures and results to ensure material performance.
- **Inspection and Testing:** Conduct non-destructive testing (NDT), hardness testing, and

chemical analysis if necessary.

Conclusion

In summary, the primary ASTM equivalent of AISI 4145 steel is ASTM A182 Grade F22, sharing similar chemical composition, mechanical properties, and applications. While other grades like ASTM A29 4140/4145 and ASTM A193 B7 can serve as substitutes depending on specific requirements, always verify compatibility through detailed specifications and testing. Understanding these equivalences ensures the right material selection, compliance with standards, and optimal performance in critical applications.

By thoroughly analyzing chemical compositions, mechanical properties, and intended uses, engineers and procurement specialists can confidently select the appropriate ASTM grade that aligns with the characteristics of AISI 4145 steel, ensuring safety, durability, and efficiency in their projects.

aisi 4145 steel astm equivalent ? this phrase encapsulates a vital link within the global steel industry, connecting a specific alloy to its standardized counterparts recognized across various standards organizations. Understanding this equivalence is crucial for engineers, manufacturers, and quality assurance professionals who rely on precise material specifications for safety, performance, and manufacturing efficiency. In this comprehensive review, we delve into the properties, applications, and ASTM equivalents of AISI 4145 steel, providing detailed insights that facilitate informed decision-making in industrial contexts.

Introduction to AISI 4145 Steel

Overview of AISI 4145 Steel

AISI 4145 is a low-alloy steel known for its high strength, toughness, and good wear resistance. It belongs to the family of 4000-series steels characterized by their alloying elements, primarily chromium and molybdenum, which enhance hardness, tensile strength, and overall durability.

This steel grade is often employed in applications requiring high fatigue strength and good machinability, such as gears, shafts, and components subjected to cyclic loads. Its composition strikes a balance between toughness and hardenability, making it a versatile choice for demanding engineering applications.

Key Properties of AISI 4145

- Chemical Composition:

- Carbon (C): 0.43?0.50%
 - Manganese (Mn): 0.60?0.90%
 - Chromium (Cr): 0.80?1.10%
 - Molybdenum (Mo): 0.15?0.25%
 - Other elements in trace amounts, such as nickel and vanadium, may be present.
-
- Mechanical Properties:
 - Tensile strength: approximately 930?1100 MPa (135?160 ksi)
 - Yield strength: around 750 MPa (109 ksi)
 - Hardness after heat treatment: 248?302 HB
 - Toughness: High impact resistance suitable for cyclic loading.
-
- Heat Treatment:
 - Typically quenched and tempered to attain desired mechanical properties
 - Can be normalized or annealed depending on application requirements.

Understanding ASTM Standards and Material Classification

What are ASTM Standards?

ASTM International (originally the American Society for Testing and Materials) develops and publishes voluntary consensus technical standards for a wide range of materials, products, systems, and services. For steels, ASTM provides specifications that define chemical composition, mechanical properties, testing methods, and manufacturing processes.

These standards ensure consistency, safety, and interchangeability of materials across different manufacturing and application sectors worldwide.

Significance of ASTM Equivalents

ASTM equivalents facilitate global commerce and manufacturing by enabling engineers and suppliers to specify materials without ambiguity. When a steel grade like AISI 4145 is referenced, identifying its ASTM equivalent ensures that the selected material meets the required standards for mechanical strength, chemical composition, and performance.

ASTM Equivalents of AISI 4145 Steel

Primary ASTM Specification for AISI 4145

The most relevant ASTM designation for AISI 4145 steel is ASTM A29 / A29M ? "Standard Specification for Steel Bars, Alloy, Standard Quality." Within this specification, AISI 4145 generally corresponds to ASTM A29 Grade 4145.

This grade covers alloy steel bars suitable for machining, forging, and heat treatment, with properties similar to those specified in AISI 4145.

Comparison of Chemical Composition

| Element | AISI 4145 | ASTM A29 Grade 4145 |

|-----|-----|-----|

| Carbon (C) | 0.43?0.50% | 0.43?0.50% |

| Manganese (Mn) | 0.60?0.90% | 0.60?0.90% |

| Chromium (Cr) | 0.80?1.10% | 0.80?1.10% |

| Molybdenum (Mo) | 0.15?0.25% | 0.15?0.25% |

| Other elements | Trace | Trace |

The close match in chemical composition indicates that ASTM A29 Grade 4145 is the primary ASTM standard equivalent.

Mechanical and Heat Treatment Standards

ASTM A29 Grade 4145 specifies mechanical properties and heat treatment procedures similar to those outlined for AISI 4145 steel. This includes:

- Quenching and tempering to achieve specified hardness and strength
- Machinability requirements
- Testing procedures for tensile, hardness, and impact properties

Other Relevant ASTM Standards and Cross-References

While ASTM A29 Grade 4145 is the main equivalent, other standards may also be relevant depending on application specifics:

- ASTM A193 / A193M ? for alloy steel bolts and studs made from similar compositions
- ASTM A320 / A320M ? for alloy steel bolting materials, including 4145 variants

Manufacturers and engineers may reference these standards for specific components such as fasteners and fittings.

Global Material Standards and Cross-References

Comparison with Other International Standards

Apart from ASTM, several other standards organizations define equivalent grades for AISI 4145 steel, including:

- EN (European Norms): EN 10083-3 42CrMo4 (similar alloy steel)
- JIS (Japanese Industrial Standards): SNCM439 (chromium molybdenum steel)
- ISO Standards: ISO 683-2 42CrMo4

These grades share similar chemical compositions and mechanical properties, allowing for cross-reference in international procurement and engineering.

Summary of International Equivalents

Standard	Grade	Composition Similarity	Typical Applications
ASTM A29 Grade 4145	4145	High	Gears, shafts, structural components
EN 10083-3	42CrMo4	Very High	Heavy-duty machinery, automotive parts
JIS SNCM439	SNCM439	High	Gear wheels, axles, crankshafts
ISO 683-2	42CrMo4	Very High	Heavy equipment, machine parts

Understanding these cross-references is vital for international projects, where compliance with multiple standards is required.

Applications and Suitability of AISI 4145 and Its ASTM Equivalent

Industrial Applications

AISI 4145 steel and its ASTM equivalent are prized for their mechanical strength, toughness, and heat treatment flexibility. Typical applications include:

- Gear manufacturing: high fatigue strength and wear resistance make it suitable for gear teeth and hubs.
- Shafts and axles: where high tensile strength and impact resistance are critical.
- Heavy machinery components: such as crankshafts, connecting rods, and pinions.
- Oil and gas industry: for drill bits and downhole tools due to toughness.

Advantages of Using ASTM Standards for Material Selection

- Global acceptance: ASTM standards are recognized worldwide, facilitating international trade.
- Consistent quality: specifications ensure uniform chemical composition and mechanical properties.
- Design confidence: engineers can rely on documented properties for safety margins.
- Ease of procurement: standardized grades simplify sourcing from multiple suppliers.

Limitations and Considerations

- Heat treatment variability: different heat treatment practices may lead to variations in properties.
- Manufacturing tolerances: adherence to ASTM tolerances is critical for performance.
- Material availability: not all suppliers may stock ASTM Grade 4145, requiring careful specification.

Conclusion and Future Outlook

The equivalence between AISI 4145 steel and ASTM A29 Grade 4145 underscores the importance of standardization in the global steel industry. Recognizing these standards enables engineers and manufacturers to select appropriate materials with confidence, ensuring performance, safety, and interoperability.

As industries evolve, so too will material standards, with increased emphasis on sustainability, advanced heat treatments, and alloy innovations. Continuous research aims to enhance the properties of low-alloy steels like 4145, expanding their applications and improving their manufacturing processes.

In conclusion, whether specified by AISI, ASTM, or international standards, AISI 4145 steel remains a vital alloy in heavy-duty engineering applications, with ASTM equivalents providing a reliable

reference framework for global procurement and engineering design. Understanding these equivalences is essential for achieving optimal performance in demanding industrial environments.

References

- ASTM International Standards
- AISI Steel Data Sheets
- European Norms (EN) Specifications
- JIS Steel Standards
- Industry Publications on Alloy Steels
- Technical Guides on Heat Treatment and Mechanical Testing

Question What is the ASTM equivalent of AISI 4145 steel? The ASTM equivalent of AISI 4145 steel is ASTM A29 4145H, which is a high-strength alloy steel used for similar applications. **What are the main properties of AISI 4145 steel that are reflected in its ASTM equivalent?** Both AISI 4145 and its ASTM equivalent possess high tensile strength, toughness, and good wear resistance, making them suitable for heavy-duty applications such as gears and shafts. **Is AISI 4145 steel the same as ASTM 4145H?** While both are similar, ASTM 4145H specifically refers to a high-strength, quenched and tempered grade of 4145 steel, aligning with AISI 4145's properties, but always verify specific requirements for your application. **Can AISI 4145 steel be substituted with ASTM 4145H in manufacturing?** Yes, ASTM 4145H is considered an equivalent and can generally be substituted for AISI 4145 steel in manufacturing, provided specifications and heat treatment processes are matched. **What are the typical applications of AISI 4145 steel and its ASTM equivalent?** Both are commonly used in the manufacturing of gears, shafts, and other components requiring high strength, toughness, and wear resistance. **Where can I find more detailed chemical composition and mechanical properties of ASTM 4145H?** Detailed information can be found in ASTM A29 standards and material datasheets, which provide comprehensive chemical and mechanical property data for ASTM 4145H steel.

Related keywords: aisi 4145 steel, astm 4145, 4145 alloy steel, 4145 steel properties, 4145 steel hardness, astm alloy standards, alloy steel grades, 4145 steel composition, heat treatable steel, alloy steel specifications

Mild steel specifications chart

mild steel specifications chart is an essential resource for engineers, architects, manufacturers, and construction professionals involved in projects requiring durable yet versatile metal materials.

Mild steel, also known as low carbon steel, is widely used across various industries due to its excellent machinability, weldability, affordability, and strength. Having a comprehensive understanding of its specifications allows for better material selection, ensuring safety, efficiency, and cost-effectiveness in construction and manufacturing processes.

In this detailed article, we will explore the key aspects of mild steel specifications, including its chemical composition, mechanical properties, grades, standards, and applications. This information, organized in a clear and accessible manner, aims to serve as a definitive guide for professionals seeking in-depth knowledge about mild steel.

Understanding Mild Steel

Mild steel is a type of carbon steel with a low carbon content, typically ranging from 0.05% to 0.25%. Its low carbon content makes it less brittle and more ductile compared to higher carbon steels, which enhances its formability and weldability.

Key Characteristics of Mild Steel:

- Good ductility and toughness
- High weldability
- Moderate strength
- Excellent machinability
- Cost-effective

Common Uses:

- Structural frameworks
- Automotive components
- Pipes and tubes
- Agricultural equipment
- General fabrication

Mild Steel Chemical Composition

The chemical composition of mild steel influences its properties and suitability for various applications. The typical chemical composition is as follows:

Element	Range (%)	Purpose/Impact
Carbon (C)	0.05 ? 0.25	Provides strength and hardness; affects ductility and weldability
Mn		

(Manganese)0.3 ? 0.9Improves hardness, tensile strength, and wear resistanceSi (Silicon)0.1 ? 0.3Deoxidizer; improves strengthP (Phosphorus)? 0.04Impacts weldability and toughness; excessive amounts reduce ductilityS (Sulfur)? 0.05Can cause brittleness; controlled to improve machinability

Note: Variations in chemical composition define different grades and standards for mild steel.

Mechanical Properties of Mild Steel

The mechanical properties determine how mild steel behaves under various loads and conditions. These properties are fundamental to ensuring that the material will perform adequately in its intended application.

Typical Mechanical Properties

Property	Value Range	Description
Tensile Strength	370 ? 700 MPa	Resistance to breaking under tension
Yield Strength	250 ? 350 MPa	Stress at which permanent deformation begins
Hardness	HRB 80 ? 100	Resistance to indentation and wear
Ductility	? 25% elongation	Ability to deform plastically before fracture
Toughness	High	Ability to absorb energy during plastic deformation

Mechanical Properties Chart

Grade	Tensile Strength (MPa)	Yield Strength (MPa)	Elongation (%)	Hardness (HB)
IS 2062 Grade A	410 ? 560	250	? 23	120 ? 170
ASTM A36	370 ? 580	250	? 23	119 ? 162

Note: Mechanical properties can vary based on manufacturing processes and heat treatments.

Mild Steel Grades and Standards

Various standards govern the specifications of mild steel, ensuring consistency and quality across industries. Some of the prominent standards include:

- IS 2062 (India): Carbon steel for general engineering purposes
- ASTM A36 (USA): Standard structural steel
- EN 10025 (Europe): Structural steels for cold-formed welded sections
- JIS G3101 (Japan): Structural carbon steel

Common Mild Steel Grades

| Grade | Standard | Typical Composition | Application |

| --- | --- | --- | --- |

| IS 2062 Grade A | IS 2062 | Carbon: 0.12%–0.22%, Mn: 0.30%–0.60% | Structural, bridges, general engineering |

| ASTM A36 | ASTM A36 | Carbon: 0.26%–0.29%, Mn: 0.60%–0.90% | Building frames, bridges |

| S235JR | EN 10025 | Carbon: 0.17%, Mn: 1.4% | Construction, mechanical applications |

Choosing the Right Grade:

- For structural applications requiring high strength, ASTM A36 or IS 2062 Grade A are common choices.
- For welding projects, grades with good weldability like IS 2062 are preferred.
- For general fabrication, standard grades as per local standards suffice.

Mild Steel Specifications Chart

Below is a comprehensive chart summarizing key specifications for common mild steel grades:

Property / Grade	IS 2062 Grade A	ASTM A36	JIS G3101 SS400
Chemical Composition (%)	C: 0.12–0.22, Mn: 0.30–0.60	C: 0.26–0.29, Mn: 0.60–0.90	C: 0.14–0.22, Mn: 0.30–0.60
Yield Strength (MPa)	250	250	235
Tensile Strength (MPa)	410 – 560	370 – 580	400 – 510
Elongation (%)	23	23	20
Hardness (HB)	120	170	119
Additional Specifications			162
			Not specified

- Thickness Range: 1 mm to 200 mm depending on the grade and application.
- Surface Finish: Usually mill finish; can be galvanized or coated for corrosion resistance.
- Weldability: Good in general, with specific grades optimized for welding.

Applications of Mild Steel

The versatility of mild steel makes it suitable for numerous applications across different industries:

- Construction: Structural beams, columns, bridges, and frameworks
- Automotive: Body panels, chassis components
- Manufacturing: Machinery parts, pipes, fasteners
- Agriculture: Fencing, tools, and equipment
- Home Appliances: Frames, enclosures

Factors to Consider When Selecting Mild Steel

Choosing the right mild steel for a project involves considering several factors:

- **Mechanical Properties:** Tensile strength, ductility, toughness
- **Chemical Composition:** To match corrosion resistance and weldability needs
- **Standards and Grades:** Compliance with regional or international standards
- **Application Environment:** Exposure to weather, chemicals, or mechanical stress
- **Cost and Availability:** Budget constraints and local supply chains

Conclusion

A comprehensive **mild steel specifications chart** is indispensable for making informed decisions in engineering, construction, and manufacturing projects. Understanding the chemical and mechanical properties, standards, and grades enables professionals to select the most suitable material for their specific needs. Whether it's for structural frameworks, automotive parts, or general fabrication, mild steel offers a reliable and economical choice.

For optimal results, always refer to the latest standards and consult with material suppliers to ensure compliance with project requirements. Proper knowledge of mild steel specifications not only enhances safety and performance but also

Mild Steel Specifications Chart: A Comprehensive Guide to Understanding Its Properties and Applications

In the realm of engineering, manufacturing, construction, and fabrication, mild steel stands as one of the most versatile and widely used materials. Its popularity stems from a combination of affordability, ease of fabrication, and satisfactory mechanical properties. To harness its full potential, understanding the detailed specifications of mild steel is vital. A mild steel specifications chart serves as an essential reference, providing comprehensive data about the material's characteristics, grades, mechanical properties, and applicable standards. This article aims to delve into the intricacies of mild steel specifications, offering an analytical perspective to help professionals and enthusiasts alike navigate this fundamental material with confidence.

Understanding Mild Steel: Definition and Basic Characteristics

Mild steel, also known as low carbon steel, typically contains a carbon content ranging from 0.05% to 0.25%. This low carbon percentage imparts specific qualities, such as ductility, weldability, and ease of machining, making it suitable for various structural and industrial applications.

Key features of mild steel include:

- High ductility and malleability: Allows for bending, shaping, and forming without cracking.
- Good weldability: Compatible with most welding processes.
- Moderate strength: Suitable for applications where high tensile strength is not the primary requirement.
- Corrosion susceptibility: Requires protective coatings or treatments when exposed to harsh environments.
- Cost-effectiveness: Less expensive compared to alloy steels, owing to its simple composition.

The basic chemical composition and mechanical properties are typically standardized across various grades and forms, but nuances exist that are critical to specific applications.

Standardization and Classification of Mild Steel

Mild steel is governed by numerous international and regional standards, which specify its chemical composition, mechanical properties, dimensions, and testing methods. Some of the prominent standards include:

- ASTM A36 (USA): One of the most common mild steel grades in North America.
- IS 2062 (India): The Indian standard for hot rolled low carbon steel.
- EN 10025 (Europe): European standards for structural steels, including mild steels.

These standards categorize mild steel into various grades based on chemical composition and

mechanical properties, which are summarized in the specifications chart.

Common classifications include:

- ASTM A36 / EN S235JR: General-purpose structural steel.
- Low Carbon Steel Grades (e.g., AISI 1015, 1020): For applications requiring specific mechanical properties.
- Hot Rolled or Cold Rolled Forms: Based on manufacturing process influencing surface finish and dimensional tolerances.

A thorough understanding of these standards enables engineers and fabricators to select the appropriate grade for their specific needs.

Key Components of a Mild Steel Specifications Chart

A mild steel specifications chart typically encapsulates vital data points that define the material's properties. These data points include chemical composition, mechanical properties, dimensions, tolerances, and applicable standards. Here's a detailed breakdown:

- Chemical Composition

This section lists the percentage of elements such as carbon (C), manganese (Mn), phosphorus (P), sulfur (S), and sometimes others like silicon (Si). For example:

| Grade | Carbon (%) | Manganese (%) | Phosphorus (%) | Sulfur (%) |

|-----|-----|-----|-----|-----|

| ASTM A36 | 0.26 max | 0.60-0.90 | 0.04 max | 0.05 max |

| IS 2062 | 0.20 max | 0.50-0.80 | 0.035 max | 0.035 max |

This composition influences the strength, ductility, weldability, and corrosion behavior of the steel.

- Mechanical Properties

Mechanical properties define how the steel responds under various loads:

Property	ASTM A36	IS 2062
-----	-----	-----
Tensile Strength (MPa)	400-550	410-560
Yield Strength (MPa)	250	245-410
Elongation (%)	23-28	23-25
Hardness (Brinell or Rockwell)	70-90 HB	Similar ranges

These parameters help determine suitability for structural or load-bearing applications.

- Physical Dimensions and Tolerances

Includes information about standard sizes, thicknesses, widths, and length tolerances, which are crucial during manufacturing and assembly.

- Forms and Finishes

Mild steel is available in various forms:

- Hot Rolled Sheets and Plates
- Cold Rolled Sheets
- Structural Sections (angles, channels, I-beams)
- Bars and Rods

Surface finishes vary from mill finish to coated or painted options.

- Standards and Certifications

A table listing the applicable standards (e.g., ASTM, ISO, EN) ensures traceability and compliance.

Detailed Analysis of Chemical Composition and Mechanical Properties

Chemical composition significantly influences the mechanical and corrosion properties of mild steel.

Carbon Content

As the primary alloying element, carbon controls the strength and hardness. Mild steels with carbon content around 0.05% to 0.25% usually balance ductility and strength. Higher carbon levels increase tensile strength but reduce weldability and ductility.

Manganese Content

Manganese acts as a deoxidizer and improves tensile strength and hardenability. Typical manganese levels in mild steel range from 0.50% to 0.80%.

Phosphorus and Sulfur

These elements are generally kept at minimal levels (max 0.035%) to prevent brittleness and improve weldability.

Mechanical Properties and Their Implications

- Tensile Strength: Ranges from 400 MPa to 550 MPa, indicating the maximum stress the steel can withstand before failure.
- Yield Strength: Usually around 250 MPa for ASTM A36, representing the stress at which permanent deformation begins.
- Elongation: Indicates ductility; higher elongation percentages suggest better formability.
- Hardness: A measure of resistance to indentation, correlating with strength.

Understanding these properties helps in selecting the right grade for load-bearing, forming, or structural applications.

Application-Driven Selection Using Specifications Chart

Choosing the appropriate mild steel grade depends on application requirements, environmental conditions, and fabrication processes.

Structural Engineering

- Grades like ASTM A36 and IS 2062 are preferred due to their favorable mechanical properties and weldability.

- Structural Sections such as beams, columns, and channels are specified based on the required load capacity and design standards.

Manufacturing and Fabrication

- Cold Rolled Sheets: Offer better surface finish and tighter tolerances, ideal for appliances, automotive panels, and decorative purposes.
- Hot Rolled Plates: Suitable for heavy-duty applications, shipbuilding, and bridges where surface finish is less critical.

Corrosion Resistance and Surface Coatings

While mild steel is inherently susceptible to corrosion, specifications charts often include options for galvanized, painted, or coated variants suitable for outdoor or marine environments.

Limitations and Considerations in Using Mild Steel

Despite its many advantages, mild steel has limitations that must be accounted for:

- Corrosion susceptibility: Requires protective coatings.
- Lower strength compared to alloy steels: Not suitable for high-stress applications.
- Thermal expansion: Needs consideration in design for thermal stresses.
- Weldability vs. Hardness: Higher strength grades may require special welding procedures.

Understanding these limitations through detailed specifications ensures safe and efficient application.

Future Trends and Innovations in Mild Steel Specifications

Advancements in steel production and processing continue to influence mild steel specifications:

- Enhanced corrosion resistance: Development of coated or alloyed mild steels.
- Environmental considerations: Eco-friendly manufacturing processes and recyclable materials.
- Precision in tolerances: Improved standards for dimensional accuracy, especially in cold rolling.
- Custom grades: Tailored specifications for specific industry needs, including seismic-resistant grades or high ductility variants.

These trends emphasize the importance of staying updated with the latest specifications chart to

optimize material selection.

Conclusion: The Significance of a Mild Steel Specifications Chart

A mild steel specifications chart is indispensable for engineers, architects, manufacturers, and quality control professionals. It provides a clear, organized, and detailed overview of the material's properties, standards, and suitable applications. By thoroughly understanding the data within these charts, professionals can make informed decisions, ensuring structural integrity, safety, and cost-effectiveness.

In a broader context, the continuous evolution of standards and specifications reflects the dynamic nature of industrial needs and technological advancements. As industries demand more specialized and durable materials, the importance of comprehensive, accurate, and up-to-date mild steel specifications cannot be overstated. Whether designing a skyscraper, manufacturing automotive parts, or constructing a bridge, referencing a detailed specifications chart is fundamental to achieving success in any project involving mild steel.

In summary, mastering the details within a mild steel specifications chart empowers stakeholders to optimize material selection, enhance product quality, and ensure compliance with industry standards, thus supporting innovation and sustainability across diverse sectors.

Question What is a mild steel specifications chart? A mild steel specifications chart is a visual reference that details the mechanical properties, chemical composition, and standard dimensions of mild steel, helping engineers and manufacturers select the appropriate grade for their applications. **Answer** What are the common grades of mild steel listed in the specifications chart? Common mild steel grades include ASTM A36, IS 2062, S235JR, and EN 10025 S235JR, each with specific properties suitable for various structural and engineering purposes. How does the chemical composition vary across different mild steel grades in the chart? The chemical composition varies mainly in carbon content and alloying elements like manganese, sulfur, and phosphorus, which influence the steel's strength, ductility, and weldability as shown in the chart. What mechanical properties are typically included in a mild steel specifications chart? The chart usually includes tensile strength, yield strength, elongation, hardness, and impact resistance, providing a comprehensive overview of the steel's performance characteristics. Why is it important to consult a mild steel specifications chart before selecting material? Consulting the chart ensures the selected mild steel meets the required strength, ductility, and other properties for your specific application, preventing material failure and ensuring safety. Can a mild steel specifications chart help determine the welding compatibility of different grades? Yes, the chart provides information on weldability and suitable welding techniques for various mild steel grades, aiding in proper fabrication processes. How are the dimensions and tolerances represented in a mild steel specifications chart? The chart displays standard dimensions, thicknesses, and permissible tolerances based on industry standards like ASTM or IS, assisting in precise manufacturing and fitting. Are the properties in the mild steel

specifications chart applicable internationally? While many properties are standardized, it's important to check the specific standards (like ASTM, EN, or IS) referenced in the chart to ensure compatibility across different regions. How can I interpret the units used in a mild steel specifications chart? Units typically include MPa or N/mm² for strength properties and percentages for elongation, with the chart providing clear labels to facilitate accurate interpretation. Where can I find a reliable mild steel specifications chart online? Reliable sources include manufacturer datasheets, industry standards organizations like ASTM or BIS, and engineering material reference websites that provide updated and detailed charts.

Related keywords: mild steel grades, steel tensile strength, steel hardness chart, steel chemical composition, structural steel standards, steel mechanical properties, mild steel applications, steel thickness chart, steel surface finish, steel hardness comparison

Ms 4361 steel equivalent

ms 4361 steel equivalent

ms 4361 steel equivalent is a critical consideration in the manufacturing, engineering, and construction industries where material selection influences the durability, strength, and performance of products. MS 4361 is a standard designation used primarily in certain regions, notably India, to specify a particular grade of steel with defined chemical composition and mechanical properties. Understanding its equivalents is essential for engineers, procurement specialists, and manufacturers who seek to source alternative materials that meet the same standards and performance criteria. This comprehensive guide explores the details of MS 4361 steel, its properties, and its international equivalents to facilitate informed decision-making in various industrial applications.

What is MS 4361 Steel?

MS 4361 is a standard specification for a specific grade of medium carbon steel. It is primarily used in manufacturing mechanical parts, shafts, gears, and other components requiring good strength, toughness, and wear resistance. The steel grade is characterized by its chemical composition, hardness, and mechanical properties, which make it suitable for applications demanding high strength and durability.

Chemical Composition of MS 4361 Steel

The typical chemical composition of MS 4361 steel includes:

- Carbon (C): 0.40% ? 0.60%
- Manganese (Mn): 0.60% ? 1.00%
- Silicon (Si): Up to 0.40%
- Phosphorus (P): Up to 0.025%
- Sulfur (S): Up to 0.035%

The specific composition may vary slightly depending on the manufacturer and application requirements. The steel's carbon content imparts hardness and strength, while manganese enhances hardenability and toughness.

Mechanical Properties

- Tensile strength: Generally ranges from 370 MPa to 600 MPa
- Hardness: Typically around 170-210 HB (Brinell Hardness)
- Toughness: Good impact resistance when properly heat-treated
- Ductility: Moderate, suitable for machining and forming processes

Applications of MS 4361 Steel

MS 4361 steel is widely used in manufacturing:

- Shafts and axles
- Gears and pinions
- Mechanical parts subjected to wear and fatigue
- Forgings and machined components
- Agricultural and construction machinery parts

Its combination of strength, toughness, and machinability makes it a versatile choice for various industrial applications.

Why Knowing MS 4361 Steel Equivalents Is Important

Understanding the equivalents of MS 4361 steel is crucial for several reasons:

- Cost Optimization: Sourcing alternative steels with similar properties can reduce manufacturing costs.
- Global Procurement: When importing materials, knowing international equivalents ensures compatibility and compliance.

- Design Flexibility: Engineers can select from a broader range of materials without compromising performance.

- Availability: Sometimes, MS 4361 steel may have limited availability; knowing equivalents helps maintain production schedules.

International Equivalents of MS 4361 Steel

Different countries and standards organizations define similar steels with varying designations. Here's an overview of some common equivalents:

- ASTM (American Society for Testing and Materials) Equivalents

Standard	Steel Grade	Composition & Properties
----------	-------------	--------------------------

-----	-----	-----
-------	-------	-------

ASTM A29	1045	Medium carbon steel with similar carbon content, good strength, and machinability
----------	------	---

ASTM A193	Grade B7	High-strength alloy steel, used in fasteners and high-temperature applications (for comparison)
-----------	----------	---

- SAE (Society of Automotive Engineers) / AISI (American Iron and Steel Institute)

Grade	Corresponding Steel	Notes
-------	---------------------	-------

-----	-----	-----
-------	-------	-------

SAE 1045	AISI 1045	Similar medium carbon steel, widely used in mechanical parts, shafts, gears
----------	-----------	---

- European Standards (EN)

Standard	Steel Grade	Equivalent Type	Notes
----------	-------------	-----------------	-------

-----	-----	-----	-----
-------	-------	-------	-------

EN 10083-2	42CrMo4	Alloy steel with similar strength and toughness, often used as an
------------	---------	---

alternative in high-stress components |

| EN 10083-1 | C45 | Medium carbon steel with comparable properties |

- JIS (Japanese Industrial Standards)

| Standard | Steel Grade | Equivalent | Notes |

|-----|-----|-----|-----|

| JIS G4051 | S45C | Similar medium carbon steel, used in machinery components |

How to Select the Right Equivalent Steel

When choosing an equivalent to MS 4361 steel, consider the following factors:

- Chemical Composition: Ensure the alloying elements match required specifications.
- Mechanical Properties: Tensile strength, hardness, toughness, and ductility should meet application demands.
- Heat Treatment Capabilities: Compatibility with heat treatment processes like quenching and tempering.
- Standards Compliance: Verify that the alternative steel complies with relevant standards for the intended application.
- Availability and Cost: Consider the local availability and cost implications.

Heat Treatment and Machinability of MS 4361 and Its Equivalents

Proper heat treatment enhances the mechanical properties of MS 4361 steel and its equivalents. Common heat treatment processes include:

- Normalization: Refines grain size and improves toughness.
- Quenching and Tempering: Increases strength and hardness while maintaining toughness.
- Carburizing: Surface hardening for wear resistance.

Machinability is generally moderate for MS 4361 and equivalent steels like 1045 or C45, making them suitable for machining operations such as turning, milling, and drilling.

Benefits of Using Steel Equivalents

- Flexibility in sourcing materials based on regional availability.
- Cost savings by choosing more economical options.
- Consistent performance when equivalents meet the same standards.
- Simplified procurement processes through knowledge of international standards.

Conclusion

Understanding the **MS 4361 steel equivalent** is essential for industries that rely on medium carbon steels for manufacturing critical components. While MS 4361 offers an excellent balance of strength, toughness, and machinability, its equivalents like ASTM 1045, JIS S45C, and European 42CrMo4 provide similar properties suitable for various applications worldwide. Selecting the right steel involves a thorough comparison of chemical composition, mechanical properties, heat treatment capabilities, and standards compliance.

By leveraging knowledge of these equivalents, engineers, procurement managers, and manufacturers can optimize costs, ensure material availability, and maintain product quality across global markets. Whether sourcing locally or internationally, understanding these standards ensures that the materials used meet the stringent demands of modern engineering and manufacturing.

Additional Resources

- Steel Standards and Specifications: Consult relevant standards organizations such as ASTM, JIS, EN, and IS for detailed specifications.
- Material Testing: Always perform mechanical and chemical testing to confirm material properties before use.
- Consult Suppliers: Engage with reputable steel suppliers for guidance on material grades and certifications.

In summary, mastering the concept of MS 4361 steel and its equivalents enables better decision-making in material selection, ensuring that components and structures perform reliably throughout their service life.

MS 4361 steel equivalent is a term that resonates deeply within the engineering, manufacturing, and materials science sectors, as it pertains to identifying steels with similar properties, compositions, and performance characteristics. As industries worldwide demand high-performance materials tailored to specific applications—from construction and automotive to aerospace and machinery—the importance of understanding steel equivalents like MS 4361 becomes paramount. This comprehensive review aims to elucidate the nature of MS 4361 steel, explore its chemical and mechanical properties, identify its international equivalents, and analyze their comparative advantages and limitations.

Understanding MS 4361 Steel

Definition and Origin

MS 4361 is a designation used primarily within the Indian standards system, particularly under the Bureau of Indian Standards (BIS). It refers to a specific grade of medium-carbon steel that is characterized by its strength, toughness, and weldability. The designation "MS" stands for "Mild Steel," though MS 4361 is more accurately classified as a medium carbon steel, often used for manufacturing components that require moderate strength and ductility.

The standard MS 4361 specifies chemical composition, mechanical properties, and permissible variations, providing manufacturers and engineers with a reliable reference point for material selection. Since the BIS standards are rooted in national requirements, they often align with or are comparable to international standards such as ASTM, EN, or JIS, leading to the development of equivalent grades across different standards.

Applications of MS 4361 Steel

MS 4361 steel finds extensive application in various sectors owing to its balanced properties:

- Automotive Components: shafts, gears, and axles requiring toughness and moderate strength.
- Structural Parts: bolts, nuts, and fasteners in construction projects.
- Machinery Parts: shafts and spindles subjected to moderate loads.
- Agricultural Equipment: plows, tines, and other parts exposed to wear.

Its popularity stems from its ease of welding, machinability, and cost-effectiveness, making it an ideal choice for medium-duty applications.

Chemical Composition and Mechanical Properties of MS 4361

Chemical Composition

The chemical makeup of MS 4361 steel typically includes the following elements (approximate ranges):

- Carbon (C): 0.30% ? 0.40%
- Manganese (Mn): 0.60% ? 0.90%
- Sulfur (S): ? 0.05%
- Phosphorus (P): ? 0.05%

- Other Elements: minor traces of silicon, nickel, chromium, and molybdenum may be present in small quantities.

The carbon content is a critical factor influencing the hardness, strength, and weldability of the steel.

Mechanical Properties

Based on the standard specifications, MS 4361 exhibits the following typical mechanical properties:

- Yield Strength: approximately 300 MPa (megapascals)
- Tensile Strength: around 480?620 MPa
- Elongation: 20% ? 25% in 50 mm gauge length
- Hardness: approximately 120?180 HB (Brinell Hardness)
- Impact Toughness: suitable for moderate impact loads

These properties make MS 4361 a versatile material, suitable for moderate to high-stress components, especially where good weldability is imperative.

International Equivalents of MS 4361 Steel

Given the widespread use of steel grades across different regions, understanding the equivalents of MS 4361 within international standards is essential for global manufacturing and procurement. Equivalence is generally established based on chemical composition, mechanical properties, and processing characteristics.

ASTM (American Society for Testing and Materials) Equivalents

The most comparable ASTM grade to MS 4361 is:

- ASTM A36 Steel

Key Similarities:

- Carbon content ranges from 0.26% to 0.29%, close to MS 4361.
- Tensile strength of 400?550 MPa.
- Good weldability and machinability.

Differences:

- Slight variations in chemical composition, especially in manganese and sulfur content.
- ASTM A36 is often considered a mild steel, but its properties align closely with MS 4361 for general purposes.

Other ASTM Grades:

- ASTM A572 Grade 50: offers higher strength but different chemical makeup.
- ASTM A529 Grade 50: similar in mechanical properties but with specific chemical variations.

European (EN) Standards Equivalents

Within the EN (European Norm) system, the following grades are comparable:

- EN 10025 S235JR

Details:

- Structural steel with yield strength of 235 MPa.
- Similar chemical composition, with controlled amounts of carbon, manganese, and other elements.
- Widely used in construction and structural applications.

Note: While S235JR has a lower yield strength than MS 4361, in terms of chemical composition and general mechanical behavior, it is considered an equivalent for many applications.

Japanese (JIS) Standards Equivalents

- JIS G3101 SS400

Features:

- Similar chemical composition with carbon around 0.16%?0.20%.
- Tensile strength of approximately 400?510 MPa.
- Widely used in construction and general engineering.

Other Notable Equivalents

Standard	Grade	Approximate Chemical Composition	Mechanical Properties	Remarks
ASTM	A36	C: 0.26-0.29%, Mn: 0.60-0.90%	Tensile: 400-550 MPa	Widely used, versatile
EN	S235JR	C: 0.17-0.20%, Mn: 1.40-1.70%	Tensile: 370-510 MPa	Suitable for structural work
JIS	SS400	C: 0.16-0.20%, Mn: 1.20-1.60%	Tensile: 400-510 MPa	Good weldability

Comparative Analysis of MS 4361 and Its Equivalents

Chemical Composition Variations

While the grades listed as equivalents share similar chemical compositions, subtle differences can influence their performance:

- Carbon Content: Slightly lower in some standards (like JIS SS400) which can result in reduced strength but enhanced weldability.
- Manganese: Variations can affect hardenability and tensile strength.
- Sulfur and Phosphorus: Kept minimal across all grades to ensure ductility and weldability.

Mechanical Properties and Performance

In general, the mechanical properties of these equivalents are comparable, with tensile strengths around 400-550 MPa and yield strengths near 235-300 MPa. However, specific application requirements may necessitate choosing a grade with higher or lower properties.

Weldability and Machinability

All grades exhibit good weldability, but higher carbon contents or alloying elements may require preheating or post-weld heat treatments. MS 4361 and ASTM A36 are renowned for their ease of welding, making them suitable for fabrication.

Cost and Availability

- MS 4361: Readily available in India and neighboring regions, often at a cost-effective rate.
- ASTM A36: Widely available globally, often at competitive prices.

- EN S235JR and JIS SS400: Common in Europe and Japan, respectively, with good supply chains.

Considerations When Selecting an Equivalent Steel

Choosing the appropriate steel grade requires a nuanced understanding of application-specific parameters:

- Mechanical Requirements: Tensile strength, yield strength, toughness.
- Weldability: Ease of welding, susceptibility to cracking.
- Corrosion Resistance: Not typically a concern for MS 4361 unless specified.
- Cost and Availability: Local supply chains and procurement costs.
- Standards Compliance: Ensure that the chosen grade meets project specifications and standards.

Conclusion and Final Thoughts

The term MS 4361 steel equivalent encapsulates a critical aspect of materials engineering: the ability to identify and utilize alternative materials that match specific performance criteria. Recognizing the equivalent grades—such as ASTM A36, EN S235JR, and JIS SS400—enables engineers and manufacturers to optimize sourcing, reduce costs, and ensure quality across international projects.

While these grades share core similarities, it remains essential to analyze their detailed chemical compositions and mechanical properties in relation to the intended application. Factors like weldability, machinability, and environmental conditions influence the final selection.

In a globalized manufacturing landscape, understanding steel equivalencies like MS 4361 not only facilitates seamless material interchange but also fosters innovation and efficiency. As industries evolve, ongoing research and standardization efforts will continue to refine these equivalences, ensuring that materials meet the demanding needs of modern engineering.

Key Takeaways:

- MS 4361 is a medium-carbon steel primarily used in India, with properties suitable for general engineering applications.
- International equivalents like ASTM A36, EN S235JR, and JIS SS400 offer comparable performance.
- Material selection should consider chemical composition, mechanical

QuestionAnswer What is the equivalent of MS 4361 steel in other international standards? MS 4361 steel is primarily equivalent to ASTM A283 Grade C and similar low to medium carbon steels used in structural applications. Can MS 4361 steel be replaced with standard ASTM steels for structural purposes? Yes, MS 4361 steel can often be replaced with ASTM A283 Grade C, but it's essential to verify mechanical properties and specifications before substitution. What are the key properties of MS 4361 steel compared to its equivalents? MS 4361 steel exhibits moderate tensile strength, good weldability, and corrosion resistance, similar to ASTM A283 Grade C, making it suitable for structural applications. Is MS 4361 steel suitable for structural engineering projects? Yes, MS 4361 steel is commonly used in structural engineering due to its strength and weldability, and it is often considered equivalent to ASTM A283 Grade C. How do I determine the chemical composition of MS 4361 steel and its equivalents? Refer to the official standards documents for MS 4361 and ASTM A283 Grade C to compare chemical compositions, focusing on carbon, manganese, phosphorus, sulfur, and other alloying elements. Are there any differences in mechanical properties between MS 4361 steel and its equivalents? While they are similar, slight variations may exist; always check specific grade datasheets to ensure mechanical properties meet your project requirements. Where can I find certified suppliers for MS 4361 steel and its equivalents? Certified steel suppliers and distributors specializing in structural steels can provide MS 4361 and equivalent grades like ASTM A283 Grade C; consult local steel standards organizations for recommendations.

Related keywords: MS 4361 steel, steel grade MS 4361, equivalent to ASTM steel, MS 4361 properties, MS 4361 hardness, MS 4361 composition, steel standards MS 4361, MS 4361 comparison, alloy MS 4361, steel grade equivalents